


CLAIMS:

1. A photopolymerization initiator comprising (A) an α -diketone compound, (B) an amine compound and (C) an s-triazine compound having a trihalomethyl group as a substituent, the amine compound (B) containing (B1) an aliphatic amine compound and (B2) an aromatic amine compound.

2. A photopolymerization initiator according to claim 1, wherein the aliphatic amine compound (B1) has a tertiary amino group in which three saturated aliphatic groups are bonded to a nitrogen atom, and at least two of said saturated aliphatic groups have electron attractive groups as substituents.

3. A photopolymerization initiator according to claim 2, wherein the aromatic amine compound (B2) is represented by the following general formula,



wherein R¹ and R² are, independently from each other, alkyl groups, and R³ is an alkyloxycarbonyl group.

4. A photopolymerization initiator according to claim 1, wherein the s-triazine compound (C) has, as a substituent, an organic group that has an unsaturated bond capable of conjugating with the triazine ring.

5. A photopolymerization initiator according to claim 1, wherein the aliphatic amine compound (B1) and the aromatic amine compound (B2) are contained at a mass ratio of B1:B2 = 3:97 to 97:3.

6. A photopolymerization initiator according to

claim 5, wherein the amine compound (B) is contained in an amount of 10 to 1000 parts by mass and the s-triazine compound (C) is contained in an amount of 5 to 1000 parts by mass per 100 parts by mass of the α -diketone compound (A).

7. A dental photopolymerizable composition blended with the photopolymerization initiator of claim 1.

8. A photopolymerizable dental composite resin of the one-paste type containing the photopolymerization initiator of claim 1, a radically polymerizable monomer without acid group (D) and an inorganic filler (E).

15

20

25

30

35